## POREX<sup>®</sup> Virtek<sup>™</sup> PTFE Materials

## PMG20

100%	CAS No. 9002-84-0
Min 500, Typical 765	mbar
Min 5, Typical 17	l/hr/cm² Δp 70mbar
0.10	mm ±0.03mm
V-0, f2	UL 94, UL746C
0.2µ	IEST RP-CC007.2 2009
	Min 500, Typical 765 Min 5, Typical 17 0.10 V-0, f2

The values stated above for Airflow and WEP are based on Porex QC test methods - Information available on request. Testing is not to any national or international standard. Different test methods and equipment may produce different results.

\* Values based on representative sample. Testing is not conducted as part of the roll approval process.

Samples are intended for evaluation purposes only and not intended for specification.

## **Additional Information**

- Can be supplied in format of:
- Master rolls (330 ±5mm width) on 75mm (3") plastic core
- Slit rolls on a 75mm (3") plastic core
- Die cut shapes
- Assembly Suggestions:
  - Ultrasonic welding
  - Thermal welding
  - Over-moulding
  - Pressure Sensitive Adhesive
  - Compression seal
- Raw material is compliant with:
  - PFOA Free, Compliant with (EC) No 1907/2006 REACH and Persistent Organic Pollutants (POP) EU 2019/1021.
  - Compliant with RoHS, WEEE, REACH
  - Operating temperature range: -40 to 260°C
  - Passes salt fog test: Test Method ASTM B117-11



Naturally hydrophobic





